

PROVISIONAL TECHNICAL DATA SHEET



Issued date: May 2025

GTPRENE ECO OC 12 BK 800

Description	Pelletized polypropylene copolymer (PP), made from recycled material.			
Color	Black			
Applications	Components for automotive, Industrial applications, Pallets			
Processing Technology	Injection			
Physical Properties	Values	Unit	ISO	ASTM D
Density	0.91	g/cm ³	1183	792
Filler Content	-	%	3451	5630
Melt Flow Index 230°C/2.16 kg	12	g/10min	1133	1238
Melting Point (DSC)	-	°C	3146	3418
Mechanical Properties	Values	Unit	ISO	ASTM D
Tensile strength at yield	-	MPa	527-1	638
Flexural Strength at yield	-	MPa	178	790
Flexural Modulus	1200	MPa	178	790
IZOD Impact strength, notched (23°C)	-	lb-ft/in2	-	256
IZOD Impact strength, notched (23°C)	8	KJ/m2	180 1eA	-
Thermal Properties	Values	Unit	ISO	ASTM D
HDT method B (0.450 MPa)	-	°C	75-1	648
Heat Aging at 150°C	-	h	Internal	
Flammability	Values			
Flame rating at 3.2 mm	HB		UL94	UL94
Processing Conditions	Values			
Drying	2h/80°C	-	-	-
1st Zone	230°C	-	-	-
2nd Zone	235°C	-	-	-
3rd Zone	240°C	-	-	-
Mold	30 - 60°C	-	-	-

Notes: The values are to be considered typical and do not constitute a specification.**Test Temperature:** 23°C, unless otherwise stated**Storage, transportation and handling:**

Storage and handling of the resin should consider protecting it from direct sunlight, temperatures above 40°C, and ambient humidity. Exposure to any of these conditions will reduce the resin's storage time.

Transport and handling equipment must be designed and equipped with the necessary measures to prevent the creation and accumulation of fine particles and dust originating from or contained in the resin. Under certain circumstances, these particles can pose a hazardous risk.

© 2024 GT+materials

The values indicated in this document are approximate, which are based on general molding conditions and are used only for the purpose of general material processing and therefore do not include an implied warranty. It is the responsibility of the user or customer to test and evaluate whether the product or material adapts to the application and environment in which it is intended to be used. Therefore, GT+materials and its subsidiaries, affiliates or related companies will not be responsible for any damage, injury or loss arising from any incorrect or defective use of the products or materials. The information contained in this document is confidential and intended only for the recipient. Unauthorized distribution, copying or use of this information is prohibited.